



PRODUCT DESCRIPTION

DRYDENE AQUALORICA™ LT is a water-based corrosion inhibitor designed for short-term protection of ferrous and non-ferrous metals components against rust for up to 1 year indoor storage. The inhibitor formula is borate, petroleum and VOC-free for improved operator safety.

PRODUCT APPLICATION

DRYDENE AQUALORICA LT should not be used at a concentration rate above 25% by volume.

When Paint will be Applied:	1 - 3%BV
Long-Term Internal Corrosion Protection:	5 - 20%BV
Recommended starting concentration:	5% BV
Operating range:	70-170° w/o foam

It can be easily cleaned from parts and surfaces with water and an alkaline cleaner.


FEATURES AND BENEFITS

DRYDENE AQUALORICA LT does not contain any petroleum content and will not leave a tacky film behind when dried. Its low-foaming formula is extremely stable and does not interfere with paint adhesion or gauging measurements.

Aqualorica LT contains powerful corrosion inhibitors that help protect ferrous, brass, bronze and copper metals.



TYPICAL TECHNICAL PROPERTIES



PROPERTY	TEST METHOD	AQUALORICA™ LT
Color	Visual	Amber
Appearance	Visual	Clear liquid
Odor	Physical	Mild
pH, 5% solution	ASTM D1172	9.1
Specific Gravity	ASTM D891	1.03
Phosphate Content		none
Biodegradability		100%

This product is not expected to have any adverse health implications when used for its intended purposes. Always wear protective gloves when handling used oil and dispose of properly. Avoid contact with skin and wash immediately with soap and water should any contact occur. Always follow manufacturers recommendations for fluid viscosity and service category. RelaDyne assumes no responsibility for product misuse or improper application. For a copy of this product's Safety Data Sheet (SDS), visit www.DRYDENE.com Rev (0422-01)